


Spray'N'Seal™

Premium Aerosol Sealer



How it works: The **Aqua Seal STS™** Product Trouble Shooting Guide covers the most common application issues and problems associated with each **Aqua Seal STS™** product.

Problem: If the product problem you are experiencing is not covered by the Product Trouble Shooting Guide then it is most likely job specific. Please contact **Aqua Seal STS™** direct for more detailed advice and information.

Solutions: The solutions described are not necessarily the only way to solve the specific problem. They are based on giving you the most efficient & direct solution without resorting to more complex solutions that may require a professional trades person. If the solutions outlined do not solve the problem it is most likely job specific. Please contact **Aqua Seal STS™** direct for more detailed advice and information.

Note: Always read entire product label, SDS & product technical bulletin before using. Do a test area first.

Problem	Reason	Solution
Visible residue on surface / streak marks show on surface.	<ul style="list-style-type: none"> Too much sealer applied. Surface not wiped completely dry after 5-10 minutes of applying sealer. Excess sealer / residue not completely wiped dry or removed. Spray'N'Seal™ has been applied over another sealer. 	<ul style="list-style-type: none"> Use cold water with MicroScrub™ and white pad. If another sealer has been previously applied, it will need to be stripped with Strip-It™ before re-applying Spray'N'Seal™.
Sealer / surface turns white or patchy.	<ul style="list-style-type: none"> Surface was wet/damp before sealing. Spray'N'Seal™ exposed to water or moisture before full cure. Excess sealer / sealer residue not completely wiped dry or removed. Spray'N'Seal™ has been applied over another sealer. Spray'N'Seal™ has been applied over surface when surface too hot or too cold. 	<ul style="list-style-type: none"> Use hot water with MicroScrub™ and white pad. Allow to dry completely and re-apply sealer. If another sealer has been previously applied, it will need to be stripped with Strip-It™ before re-applying Spray'N'Seal™. Patchy effect might not be reversible. Mechanical removal may be required.
Surface water beading reduces after a few weeks.	<ul style="list-style-type: none"> This is normal as the surface tension created by the sealer is worn off leaving the active sealer below the surface of the stone or tile. There is no need to re-seal. 	<ul style="list-style-type: none"> N/A
Sealer effect disappears after heavy duty cleaning.	<ul style="list-style-type: none"> Not enough sealer applied. Harsh cleaning methods, pressure washing, high alkaline, acidic or solvent based cleaners or weather exposure will affect wear & performance. Exterior, high use or high traffic areas may require more frequent applications. 	<ul style="list-style-type: none"> Only maintain sealed surface with pH neutral cleaners such as EzyClean™ or Boost™ Re-apply Spray'N'Seal™ as required.
Sealer does not bead water even after several applications.	<ul style="list-style-type: none"> Sealer has not cured because surface is too damp. Surface has been previously cleaned with an incompatible cleaner such as acid. 	<ul style="list-style-type: none"> Reseal after surface has properly dried. If an incompatible cleaner has been used, clean floor with EzyClean™, rinse well with water and allow to thoroughly dry before resealing.
Surface darkens after sealing.	<ul style="list-style-type: none"> Solvent carrier can slightly darken some surfaces. 	<ul style="list-style-type: none"> N/A