

Tender specifications

CLUNY KERLITE 3plus collection

Supply of ceramic tiles made of Cotto d'Este Kerlite laminated porcelain tile for floors and walls.

Product characteristics

Cotto d'Este Kerlite laminated porcelain tiles, produced in a maximum size of 3000x1000 mm and 3mm thick, reinforced with fibreglass mesh, obtained from raw materials of the highest quality and purity (light clay, feldspar and ceramic pigments with high chromatic performance), and manufactured by dry pressing on a belt of atomized powder, subsequently sintered by means of industrial firing at temperatures exceeding 1200 °C.

The innovative Kerlite manufacturing process produces a final product which is light, flat and flexible, but at the same time compact, non-absorbent, frost-resistant, resistant to stains, chemical attack and thermal shock. The application of the fibreglass mesh gives the product high resistance and extreme versatility and ease of use for a wide range of applications in the architectural world.

Compliance with EN 14411-G / ISO 13006-G

The Cluny Kerlite 3plus collection is in compliance with the regulations required for first quality products in Italy and Europe UNI EN 14411-G and internationally through ISO 13006-G.

Quality and environmental certifications

The conservation of the product characteristics is guaranteed by the Quality Management System put into practice by Cotto d'Este in its plants and certified in accordance with UNI EN ISO 9001.

The collection is manufactured in plants with UNI EN ISO 14001 certified Environmental Management Systems (internationally recognised standard) and EMAS (Regulation 1221/09 - eco-management and audit community system).

The collection helps to meet the criteria for obtaining LEED credits. The product contains no VOC (volatile organic compounds) and has obtained the GREENGUARD GOLD certification. The Environmental Product Declaration (EPD) is available, this tool communicates clearly the environmental performances of the Cluny Kerlite 3plus collection based on its Life Cycle Assessment (LCA).

Antibacterial properties

Thanks to Protect antibacterial technology, the tiles from the Cluny Kerlite 3plus collection have continuous, effective and durable protection against the proliferation of bacteria, tested and certified in accordance with ISO 22196 and ASTM E3031

Commercial description of the product	
Company	COTTO D'ESTE (Panariagroup Industrie Ceramiche S.p.A.)
Collection	CLUNY KERLITE 3plus
Colours	ARGEROT, AUVERGNE, BOURGOGNE, CHAMPAGNE
Sizes	100X100cm
	100X300cm
Surfaces	NATURAL
Edges	RECTIFIED
Thickness	3,5mm



**Tender specifications
CLUNY KERLITE 3plus collection**

Technical features

Product type: laminated porcelain stoneware (UGL)

According to: ISO 13006-G (Group Bla), EN 14411-G (Group Bla)

Technical features	Test method	Required values ISO 13006-G, EN 14411-G	Average values CLUNY KERLITE 3plus
Water absorption	ISO 10545-3	$\leq 0,5\%$	0,1 (*) %
Modulus of rupture	ISO 10545-4	$\geq 35\text{ N/mm}^2$	50 N/mm ²
Deep abrasion resistance	ISO 10545-6	$\leq 175\text{mm}^3$	175mm ³
Linear thermal expansion	ISO 10545-8	No provision	$\alpha \leq 7 \cdot 10^{-6}\text{ }^{\circ}\text{C}^{-1}$
Stain resistance	ISO 10545-14	Class 3 Min.	5 RESISTANT
Chemical resistance (**)	ISO 10545-13	As indicated by manufacturer	LA, HA RESISTANT
Frost resistance	ISO 10545-12	No alteration	RESISTANT
Dimensions	Lenght and width	ISO 10545-2	$\pm 0,3\%$, max $\pm 1\text{ mm}$
	Straightness of sides	ISO 10545-2	$\pm 0,3\%$, max $\pm 0,8\text{ mm}$
	Rectangularity	ISO 10545-2	$\pm 0,3\%$, max $\pm 1,5\text{ mm}$
	Warpage	ISO 10545-2	$\pm 0,4\%$, max $\pm 1,8\text{ mm}$
	Thickness	ISO 10545-2	$\pm 5\%$, max $\pm 0,5\text{ mm}$
Slip resistance		DIN 51130	-
		BCR-TORTUS	-
		ANSI A326.3	$\mu > 0,40$
Shade variation		ANSI A326.3	DCOF ≥ 0.42
Fire reaction		EN 13823	Class A2-s1,d0 (wall)
		EN 9239-1	Class A2 _{fl} -s1 (floor)
Thermal conductivity		EN 12524	$\lambda = 1,3\text{ W/m }^{\circ}\text{K}$
Recommended minimum joint (***)		Indoor	1mm (wall) 2mm (floor)

(*) Average value referred to ceramic material only.

(**) Excluding hydrofluoric acid and its derivatives.

(***)The width of grout joints must be established by the installation supervisor, unless grout widths are regulated by national laying standards.

